

Product data sheet 841-1-2



Page 1 of 3 / As at: 04-2018

Certification number: 1724 - CPR - 041101
1724 - CPR - 041201

Product trade name: **SK Bit 105® PV Root Protection Membrane
polymer bitumen torch-on membrane**

Product-number: 11642

Product-standard: DIN EN 13707
DIN EN 13969

Labelling: DO / E 1 PYE-PV 200 S5 acc. to DIN SPEC 20000-201
BA / PYE-PV 200 S5 acc. to DIN SPEC 20000-202

Length, width: 5.00 m x 1.08 m
Thickness: 5.20 mm Coating type: Polymer bitumen
Content of solubility: N/A
Reinforcement: Polyester fleece
Min. weight of reinforcement: 250 g/m²

Polymer bitumen torch-on membrane with polyester fleece as a top layer of roof insulation.

Characteristics according to DIN EN 13 707, DIN EN 13 969	Test method/ Classification	Units	Requirements/ Critical Value
Visible defects	DIN EN 1850-1	-	no visible defects
Length	DIN EN 1848-1	m	≥ 5,00
Width	DIN EN 1848-1	m	≥ 1,08
Straightness	DIN EN 1848-1	mm/10 m	≤ 20
Mass per unit area	DIN EN 1849-1	kg/m ²	unverifiable result
Thickness	DIN EN 1849-1	mm	≥ 5,20
Water tightness at 200 kPa test pressure	DIN EN 1928 method B	-	passed
External fire performance	DIN V ENV 1187	-	see testing of system
Reaction to fire	DIN EN ISO 11925-2	-	Class E according to DIN EN 13501-1
Water tightness after stretching at low temperatures	DIN EN 13897	-	unverifiable result
Peel resistance of joint	DIN EN 12316-1	N/50 mm	unverifiable result
Shear Resistance of joint	DIN EN 12317-1	N/50 mm	unverifiable result
Tensile properties: maximum tensile force	DIN EN 12311-1	N/50 mm	1200 / 1000 ± 10 %

GEORG BÖRNER


Chemisches Werk für Dach- und
Bautenschutz GmbH & Co. KG

Heinrich-Börner-Straße 31
D-36251 Bad Hersfeld

Tel. +49 (0)6621 175-0
Fax +49 (0)6621 175-200

Info@GeorgBoerner.de
www.GeorgBoerner.de

Reserving changes. The indicated technical values refer to the date of production.



Product data sheet 841-1-2

Page 2 of 3 / As at: 04-2018

Certification number: 1724 - CPR - 041101
1724 - CPR - 041201



Characteristics according to DIN EN 13 707, DIN EN 13 969	Test method/ Classification	Units	Requirements/ Critical value
Tensile: Elongation	DIN EN 12316-1	%	40 / 45 \pm 5 abs.
Resistance to impact	DIN EN 12691	mm	unverifiable result
Resistance to static loading	DIN EN 12730	kg	unverifiable result
Resistance to tearing (nail shank)	DIN EN 12310-1	N	unverifiable result
Resistance to root penetration	DIN EN 13948	-	root resistance
Dimensional stability	DIN EN 1107-1	%	-
Form stability under cyclic temperature change	DIN EN 1108	%	unverifiable result
Flexibility at low temperatures	DIN EN 1109	°C	\leq - 25
Flow resistance at elevated temperatures	DIN EN 1110	°C	\geq + 115
Artificial aging DIN EN 1296	DIN EN 1109 or DIN EN 1110	°C °C	unverifiable result unverifiable result
Adhesion of granules	DIN EN 12039	%	-
Water vapour transmission properties	DIN EN 1931	-	-

Customer Information:

Purpose:

SK Bit 105® PV root protection membrane is the top sealing layer and as such a reliable root protection on an intensive or extensive green flat roof. The sheet – with polyester fleece reinforcement – possesses polymer bitumen covering layers with root resisting additives. The 4 year lasting tests were passed according to the FLL standards at the Botanic Institute Hamburg. Test certificates are available on request.

GEORG BÖRNER


Chemisches Werk für Dach- und
Bautenschutz GmbH & Co. KG

Heinrich-Börner-Straße 31
D-36251 Bad Hersfeld

Tel. +49 (0)6621 175-0
Fax +49 (0)6621 175-200

Info@GeorgBoerner.de
www.GeorgBoerner.de

Reserving changes. The indicated technical values refer to the date of production.



Product data sheet 841-1-2

Page 3 of 3 / As at: 04-2018

Certification number: 1724 - CPR - 041101
1724 - CPR - 041201



Application:

The processing of **SK Bit 105® PV root protection membrane** is carried out in accordance with DIN 18531, the valid "Regulations for roofs with sealant – flat roof regulations" and the "abc of bitumen membranes" as well as DIN 18533.

The whole membrane is torched-on using a surface heating method with a minimum of 8 cm side and 10 cm end laps. The density of the joint connection has to be tested!

Loose laying or mechanical fixing of the membrane as well as spots or stripes of melting/adhesion on the surface as well as melting/adhesion of the joint overlap can cause corrugation if the outside temperatures and/or surface temperatures are low.

Advice:

Please note that the colour of the granules can vary during their useful life due to the effect of the weather and other outside agents.

Chemical resistance:

SK Bit 105® PV root protection membrane is resistant to water and watery solutions of salt as well as diluted, non oxidising acids and bases. Aliphatic and aromatic hydrocarbons as well as chlorine hydrocarbons, oils and greases loosen the **SK Bit 105® PV root protection membrane**.

Storage:

Store upright in a cool and dry place.

Safety data sheet:

Supplementary safety data sheet is available on request.

GEORG BÖRNER

Chemisches Werk für Dach- und
Bautenschutz GmbH & Co. KG

Heinrich-Börner-Straße 31
D-36251 Bad Hersfeld

Tel. +49 (0)6621 175-0
Fax +49 (0)6621 175-200

Info@GeorgBoerner.de
www.GeorgBoerner.de

Reserving changes. The indicated technical values refer to the date of production.